

tesa® ACX^{plus} 7048 Gray/White 2,000 µm double-sided acrylic foam tape

tesa® ACX^{plus} 7048 is a double-sided acrylic foam tape, available in gray or white. It consists of a high performance acrylic system, and is identified by its bonding power, stress dissipation and its temperature resistance.

Due to the product's unique formulation, this double-sided acrylic foam tape combines high adhesion levels with the ability to absorb and dissipate high dynamic loads. The viscoelastic core of this product is able to compensate for thermal elongations of bonded parts.

tesa® ACX^{plus} 7048 performs well on "hard-to-bond-materials" such as powder coatings or plastic materials. Even in combinations of such materials, this product provides advanced safety due to its innovative product design. This product is especially designed to allow seamless bonding of decorative elements. The gray or white color options adapt very well to metal and plastic surfaces and avoid gleaming of translucent and decorative elements.

Main Application

The tesa® ACX^{plus} product family is suitable for a wide range of constructive bonding applications. To ensure the highest performance possible, our aim is to fully understand the application (including the substrates involved) in order to provide the right product recommendation. Example mounting applications include but are not limited to:

- Decorative panels (e.g. refrigerator glass doors)
- Decorative elements (e.g. covers of dishwashers, muntin bars on windows)
- Glass-to-glass or glass-to-metal applications (e.g. partition walls or glass doors)
- Furniture mounting
- Flush Design

Technical Data

▪ Backing material	foamed acrylic	▪ Type of adhesive	pure acrylic
▪ Color	gray/white	▪ Elongation at break	730 %
▪ Total thickness	2000 µm		

Adhesion to

▪ Steel (after 3 days)	38.0 N/cm	▪ Glass (after 3 days)	40.0 N/cm
▪ ABS (after 3 days)	55.0 N/cm	▪ PMMA (after 3 days)	33.0 N/cm
▪ Aluminium (after 3 days)	45.0 N/cm		

For latest information on this product please visit <http://l.tesa.com/?ip=07048>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

tesa® ACX^{plus} 7048 Gray/White

2,000 µm double-sided acrylic foam tape

Properties

▪ Temperature resistance short term	200 °C	▪ Resistance to chemicals	● ● ● ●
▪ Temperature resistance long term	110 °C	▪ Softener resistance	● ● ●
▪ Tack	● ● ●	▪ Static shear resistance at 23°C	● ● ● ●
▪ Ageing resistance (UV)	● ● ● ●	▪ Static shear resistance at 70°C	● ● ● ●
▪ Humidity resistance	● ● ● ●	▪ T-block	● ● ● ●

Evaluation across relevant tesa® assortment: ● ● ● ● very good ● ● ● good ● ● medium ● low

Additional Information

Please note that we recommend using tesa® Adhesion Promoter as a surface pre-treatment. It leads to a significant improvement in adhesion levels, avoids moisture infiltration, and promotes long-term resistance against harsh environmental factors. Which tesa® Adhesion Promoter should be used depends on the substrates and the application. We will be glad to advise you in order to find the right solution.

For permanent outdoor applications with load-bearing requirements, our first recommendation is tesa® ACX^{plus} 707x High Resistance.

Liner versions:

- PV26: White paper liner – unbranded
- PV28: Blue film liner – unbranded
- Further liner versions might be available upon request

For latest information on this product please visit <http://l.tesa.com/?ip=07048>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.