



tesa® 51865 - Team 4965 Differential



Product Information

165µm/6.5 mils double sided transparent PET film tape with asymmetrical product design

Product Description

- tesa® 51865 - Team 4965 Differential is a transparent, double-sided industrial mounting tape consisting of a PET backing and a tackified acrylic adhesive. The asymmetrical double-sided tape is the differential version of tesa® 4965 Original and its adhesive is based on a patented and protected product technology. The liner covered side of tesa® 51865 - Team 4965 Differential has a high coating weight for maximum flexibility and versatility on multiple surface demands. The open side has a reduced coating weight which delivers a secure bond to flat profiles laminated under controlled conditions. tesa® 51865 - Team 4965 Differential is able to withstand numerous environmental factors such as humidity, UV-light and temperatures of up to 200°C for limited periods of time. The tackified acrylic adhesive makes for an excellent hold on various surfaces, high tack, and good shear strength.

Several products are equipped with this unique and high performing product design and together these products make up Team 4965. This double-sided film tape assortment helps to easily select the most efficient tape based on customer demands, products, and processes. Explore the benefits of the full tesa® 4965 assortment here:

<https://www.tesa.com/en-us/industry/general-applications/mounting/team-4965-assortment>

Product Features

- Asymmetrical product design with superior adhesion on liner covered side
- Excellent bond to extruded trims and profiles
- Reliable bond even on low surface energy surfaces
- Immediate usability right after assembly
- High resistance to demanding environmental conditions

Application Fields

- tesa® 51865 - Team 4965 Differential is especially designed for mounting of extruded trims and profiles
- Mounting of decorative trims and profiles in the furniture industry
- Bonding in the roller blind production
- Mounting of magnetic stripes

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing material	PET film	• Total thickness	165 µm
• Type of adhesive	tackified acrylic		6.5 mils
		• Color	transparent

For latest information on this product please visit <http://l.tesa.com/?ip=51865>



tesa[®] 51865

- Team 4965 Differential

Product Information

Properties/Performance Values

• Elongation at break	55 %	• Static shear resistance at 23°C	good
• Tensile strength	20 N/cm	• Static shear resistance at 40°C	good
	11.4 lbs/in	• Tack	good
• Ageing resistance (UV)	very good	• Temperature resistance long	100 °C
• Chemical resistance	good	term	212 °F
• Humidity resistance	very good	• Temperature resistance min.	-40 °C
• Softener resistance	good		-40 °F
		• Temperature resistance short	200 °C
		term	392 °F



tesa® 51865

- Team 4965 Differential

Product Information

Adhesion to Values

• ABS (initial)	9.5 N/cm 86.8 oz/in	• PET (covered side, after 14 days)	10.5 N/cm 95.9 oz/in
• ABS (after 14 days)	10 N/cm 91.4 oz/in	• PET (covered side, initial)	10 N/cm 91.4 oz/in
• ABS (covered side, after 14 days)	13 N/cm 118.8 oz/in	• PP (initial)	7 N/cm 64 oz/in
• ABS (covered side, initial)	12 N/cm 109.6 oz/in	• PP (after 14 days)	8 N/cm 73.1 oz/in
• Aluminium (initial)	9 N/cm 82.2 oz/in	• PP (covered side, after 14 days)	8.5 N/cm 77.7 oz/in
• Aluminium (after 14 days)	9.5 N/cm 86.8 oz/in	• PP (covered side, initial)	8 N/cm 73.1 oz/in
• Aluminium (covered side, after 14 days)	12.5 N/cm 114.2 oz/in	• PS (initial)	9 N/cm 82.2 oz/in
• Aluminium (covered side, initial)	12 N/cm 109.6 oz/in	• PS (after 14 days)	11 N/cm 100.5 oz/in
• PC (initial)	9 N/cm 82.2 oz/in	• PS (covered side, after 14 days)	13.5 N/cm 123.3 oz/in
• PC (after 14 days)	12 N/cm 109.6 oz/in	• PS (covered side, initial)	12 N/cm 109.6 oz/in
• PC (covered side, after 14 days)	15 N/cm 137 oz/in	• PVC (initial)	7 N/cm 64 oz/in
• PC (covered side, initial)	13 N/cm 118.8 oz/in	• PVC (after 14 days)	11 N/cm 100.5 oz/in
• PE (initial)	6.5 N/cm 59.4 oz/in	• PVC (covered side, after 14 days)	14 N/cm 127.9 oz/in
• PE (after 14 days)	7 N/cm 64 oz/in	• PVC (covered side, initial)	9 N/cm 82.2 oz/in
• PE (covered side, after 14 days)	8 N/cm 73.1 oz/in	• Steel (initial)	9.6 N/cm 87.7 oz/in
• PE (covered side, initial)	7 N/cm 64 oz/in	• Steel (after 14 days)	11.5 N/cm 105.1 oz/in
• PET (initial)	9 N/cm 82.2 oz/in	• Steel (covered side, after 14 days)	14.5 N/cm 132.5 oz/in
• PET (after 14 days)	9.5 N/cm 86.8 oz/in	• Steel (covered side, initial)	13.3 N/cm 121.5 oz/in

Additional Information

Liner variants:

- PV2: brown glassine paper (78µm / 3.1 mils; 90g/m²)
- PV6: red MOPP-film (80µm / 3.2 mils; 72g/m²)

For spools, it is recommended to use tesa® dispensers to achieve optimal results.

For latest information on this product please visit <http://l.tesa.com/?ip=51865>



tesa[®] 51865 - Team 4965 Differential

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=51865>